



meccanocar 411 00 15125-2854-Aderfix gaskets 20 g.

PROPERTIES.

The Meccanocar Aderfix gel is a single-component cyanacrylate adhesive without solvents. It has very quick adhesion and is cold drying.

When in contact with anion initiators, Aderfix gel is quick to polymerize; in most cases, traces of humidity on the supports to be glued are enough to trigger the process of polymerization

The quick polymerization, associated to excellent adhesion of the polymer on many supports, make Aderfix gel irreplaceable for gluing almost all types of materials.

SPECIFICATIONS.

Base: Ethyl.

Viscosity: CPS): 20.

Applications: EPDM, DUTRAL.

HOW TO USE.

For obtaining the best results with Aderfix gaskets, you must consider that:

- The surfaces must be cleaned and degreased.
- The parts must fit together perfectly. In case there should be some play, we suggest you use "Aderfix gel".
- Spread a light film on one of the two parts and quickly assemble, placing slight pressure on the parts for a few minutes
- Polymerization of Aderfix gaskets occurs through the effects of humidity on the supports. The perfect conditions are: from 40% to 70% of relative humidity. Do not go below 30%.
- For gluing large surfaces, we suggest you place drops at equal points rather than a film.

Detachment of the adhesive joint:

- Should you wish to detach material glued with Aderfix gasket, you must:
- Heat at a temperature above 200°C (quick method).
- Emerge the parts in dimethylformaldehyde (toxic), or in ethyl acetate (slow method).

PRECAUTIONS OF USE:

The Aderfix gasket is not toxic, only irritating; it is thus necessary to work in ventilated environments.

The danger is that it glues rapidly, thus, in case of contact with skin or eyes, washy quickly with plenty of water and consult a physician

Absolutely keep the product away from children's reach.

STORAGE OF THE PRODUCT:

If an Aderfix gasket is stored in a dry and dark place, it lasts for a minimum of:

- 9 months at +20°C.
- 1 year at +5°C.
- Unlimited at -20°C.