

Black under-bodywork protective-Technical Data Sheet. Page 1 of 1 21/10/2010

meccanocar 411 00 14765-2765-Black under-bodywork protective

DESCRIPTION

The Meccanocar "Black under-bodywork protective" is a sintetic resin based soundproof and antistone coating, for vehicle bottom, lateral sides and other vehicle parts.

It's overpaintable, and resist to scratch, shock, and many aggressive substances.

CHEMICAL AND PHYSICAL SPECIFICATIONS

- Base: syntetic resins, solvents, plasticizings, and mineral charges.
- Colour: black.
- > Appearance: liquid.
- Viscosity at 25°C.: 16000/20000 cps.
- Specific weight: 1,31/1,32 g/cm3.
- Dried residue: 66/67%.
- Dust out at 25°C., 50% U.R.: 10 +/- 2 min.
- Overpaintable @ 25°C-ur 55%: ca 30 min.
- Resistance to saline mist: good after 100 hours.
- ➤ Temperature of use: 10/35°C.

EMPLOYMENT AND USE

Clean and degrease the surface to be treated with anti-silicone products. Passivity the surfaces with a rust prevention base, wash primer or transparent insulator. Sandpaper, and then apply the underbodywork protective product by spraying with the appropriate paint-gun. If necessary, varnish over. For best results use 2 bar air pressure.

STORAGE AND LIFE

The black under-bodywork protective, stored in its original packaging, in dry and well ventilated place, at temperatures between $+5^{\circ}C e + 30^{\circ}C$ lasts for 12 months from the manufacturing date.

NOTES

The information and values appearing on this Technical Sheet correspond to our concrete experience and technical research, without though, constituting any responsibility or guarantee on our part because, we cannot control all types of uses.

The user shall therefore determine suitability for his specific use.